

| Product | Vin con | Mooney viscosity ML (1+4) | Specific gravity | Supply Form | Packaging |
|------------------------------------|---------|---------------------------|------------------|-------------|---|
| Levapren® 400 | 40 | 20 +/- 4 | approx. 0.98 | granules | 25 kg bags*(2) on pallet, 1000 kg net or Big Bag, 700 kg net |
| Levapren® 450 | 45 | 20 +/- 4 | approx. 0.99 | granules | 25 kg bags *(2) on pallet, 1000 kg net or Big Bag, 600 kg net |
| Levapren® 500 | 50 | 27 +/- 4 | approx. 1.00 | granules | 25 kg bags *(2) on pallet, 1000 kg net |
| Levapren® 600 | 60 | 27 +/- 4 | approx. | granules | 25 kg bags *(2) in cardboard boxes on pallet, 1000 kg net |
| Levapren 650 VP*(3) | 65 | 27 +/- 4 | approx. | | |
| Levapren® 700 | 70 | 27 +/- 4 | approx. | | |
| Levapren® 800 | 80 | 27 +/- 4 | approx. | | |
| Levapren® 900 | 90 | 38 +/- 6 | approx. | | |
| ↓ Trial products, precrosslinked ↓ | | | | | |
| Levapren® 500 XL | 50 | 55 +/- 10 | approx. | granules | 25 kg polyethylene bags, in cardboard boxes on pallet, 750 kg net |
| Levapren 600 XL VP*(3) | 60 | 55 +/- 10 | approx. | | |
| Levapren 700 XL VP*(3) | 70 | 60 +/- 10 | approx. | | |
| Levapren 800 XL VP*(3) | 80 | 55 +/- 10 | approx. | | |

*(1) ISO 289/ASTM D 1646

*(2) film based on EVA-Copolymer resin, melting point 93°C, film thickness 0,13 mm

*(3) VP : Versuchsprodukt (Trial Product)

All products are supplied as granules.

Levapren® types 400-900 are standard packaged in 25 kg polyethylene bags** on pallet (1000kg net),

Levapren® XL is similar to the respective Levapren® type but have improved processing properties.

Levapren® XL comes in 25 kg polyethylene bags*** in cardboard boxes on pallet (contents 750 kg).