

INNOVATION SINCE 1908





Product lines for Hydrogen Cylinder Manufacturing

DYHARD[®]

DYHARD[®] Fluid system for hydrogen cylinder in FCEV





DYHARD[®] Fluid system based on:

DYHARD[®] RF2100:

Low viscos modified BPA epoxy resin

DYHARD[®] Fluid 212: Latent liquid curing agent

Benefits:

- Extreme long pot life
- **Continuous winding operation**

.

- Increased productivity, higher profitability
- Consistent viscosity in summer and winter
- Reduction of cleaning time and resin waste
- Excellent mechanical properties
- Low enthalpy

Viscosity versus time comparison: DYHARD[®] Fluid system at 40°C versus competitive Anhydride and Jeffamines systems at 25°C





1800 1600 Pressure (bar) 1400 Pressure (Bar) 1200 1000 800 600 400 200 0 100 200 300 400 Time (sec)

Hydrostatic burst pressure test

Sample	Resin	Hardener	Carbon fiber	Diameter (mm)	Length (mm)	Weight (g)		Fiber
						Laminate	Vessel	weight %
1905- 050-700- 009	RF2100	Fluid 212	Hyosung H2550 24k	367.2	852	32100	38400	76

TYPE 4 CYLINDER TESTS

according to ISO 11439:2013 and E/ECE/TRANS/505/Rev.2/Add.133 – 25 June 2015

Properties:

- Hydrostatic burst pressure H2-cylinder: 1727 bar = 2.46 NWP*
- Hydrostatic burst pressure CNG-cylinder: 590 bar = 2.95 NWP*
- Pressure cycle test: Passed; >60.000 cycles
- High-pressure creep test: Passed; 246 hrs. in water at 100°C (*NWP= Nominal Working Pressure)

FILAMENT WINDING

PRODUCT LINE	PRODUCTS	WET FIBER WINDING	TOWPREG
DYHARD [®] SYS-LINE	DYHARD [®] RF2100	✓	✓
	DYHARD [®] FLUID 212	✓	✓
DYHARD [®] CU-LINE	DYHARD [®] 100S	-	✓
	DYHARD [®] 100SF	-	v
DYHARD [®] MB-LINE	DYHARD [®] D50EP	-	✓
	DYHARD [®] DF50EP	-	v
DYHARD [®] CAT-LINE URONS	DYHARD [®] UR400	-	v
	DYHARD [®] UR500	-	✓
DYHARD [®] LI-LINE	DYHARD [®] FLUID 111	-	v
	and a second		The second

YOUR CONTACT IN GERMANY:

AlzChem Trostberg GmbH

Dr.-Albert-Frank-Straße 32 83308 Trostberg, Germany

T +49 8621 86-3402 F +49 8621 86-503402

info@alzchem.com

YOUR CONTACT IN THE US:

AlzChem LLC

11390 Old Roswell Road, Suite 124 Alpharetta, GA 30009

T +1 770 804-0 371 **F** +1 770 804-0 375

info@alzchem.com



WWW.ALZCHEM.COM

This information is based upon our present knowledge and experience, and is intended to provide general notes about our products and their uses. AlzChem therefore assumes no liability for such information or advice, including the suitability of such information or advice for a particular application or the extent to which such information or advice may relate to third party intellectual property rights or to laws and provisions. It is the sole responsibility of the customer to arrange for incoming products to be inspected and tested by qualified experts. Edition: 2020 (This publication supersedes all previous publications for this product group.)