

	Description	Description(和訳)	Raw Color	G.E. Brightness	pH	Specific Gravity	Surface Area (m2/g)	Median Particle size (μ)	Oil Absorption	Others
Amlok 321	Mineral Air Float Kaolin	アミノシラン処理をした風簾クレイ	White	70-80	7-9	2.6	22-26	0.3		
Mercap 100	Mineral Air Float Kaolin	メルカプトシラン処理をした風簾クレイ	White	70-80	4-5	2.6	22-26	0.3	33-38	
Mercap 200	Mineral Air Float Kaolin	メルカプトシラン処理をした風簾クレイ	White	70-80	4-5	2.6	22-26	0.3	33-38	Sharper particle size distribution than Mercap 100
Suprex	The hard kaolin, Suprex, has gained worldwide acceptance as the premier kaolin filler for the rubber industry.	風簾クレイです。ゴムの補強硬化があります。	White		4-5.5	2.6		0.3		