

# Amlok 321

## PRODUCT

Mineral | Air Float Kaolin

## TYPICAL PHYSICAL PROPERTIES

SiO <sub>2</sub>	(%)	45.1
Al <sub>2</sub> O <sub>3</sub>	(%)	38.1
Fe <sub>2</sub> O <sub>3</sub>	(%)	1.7
TiO <sub>2</sub>	(%)	1.6
K <sub>2</sub> O	(%)	0.3
Na <sub>2</sub> O	(%)	Trace
CaO	(%)	0.02
MgO	(%)	Trace
L.O.I.	(%)	13.6
Zinc	(ppm)	270
SO <sub>3</sub>	(%)	0.5
P <sub>2</sub> O <sub>5</sub>	(%)	0.1

## PHYSICAL PROPERTIES

Raw Color		White
G.E. Brightness		70- 80
pH		7-8
Specific Gravity	(%)	2.6
Surface Area	(m <sup>2</sup> /g)	22-26
Oil Absorption	(g/100g)	33-38

## PARTICLE SIZE

Median	(microns)	0.3
+325 Mesh	(% retained)	0.25
% < 20	(microns)	99
% < 10	(microns)	99
% < 5	(microns)	97
% < 2	(microns)	93
% < 1	(microns)	86
% < 0.5	(microns)	72
% < 0.2	(microns)	34

## Imerys

### Sales Office:

100 Mansell Court East,  
Suite 300  
Roswell, GA 30076  
United States

### Production Site:

Langley, SC, USA

### Customer Service:

Tel: +1 (888) 567 6548  
Fax: +1 (770) 645 3685

[www.imerys.com](http://www.imerys.com)

The data quoted here is believed to be correct and represent the typical value of this product. It is not intended to represent product specifications. Every precaution is taken to ensure the products conform to our published data, but since the products are based on naturally occurring raw materials, we reserve the right to change this data should it become necessary. All recommendations and sales are made on the condition that we will not be held liable for any damages resulting from their use. This provision may not be changed by any of our representatives. Any Health and Safety questions, please refer to our SDS.

