



EPOXYPRENE SPECIFICATION

Properties	Epoxyprene 50	Epoxyprene 25
Epoxidation level* , (mole %) *Nuclear Magnetic Resonance Spectrometer	50 ± 2	25 ± 2
Glass Transition temperature , (C)	-24	-47
Mooney viscosity* ML(1'+4') 100 C *or Customer requirement	70-100	70-100
Ash content (% by weight)	0.50 max	0.50 max
Density, Mg/m ³	1.02	0.97
Lovibond colour	3.5	4.5



MUANG MAI GUTHRIE
Public Company Limited.