

Keltan name	ML1+4		ML1+8		MFI 190°C/ 2.16kg	Composition				Bale form	weight kg/pallet
	100°C	125°C	100°C	150°C		% Diene		% C 2	Oil (phr)		
						ENB	DCPD				
Copolymers											
3050	51							49			900
Copolymers (REX grades)											
1500R		10			2.55			49		22.7kg	681
0500R		2			11			49		22.7kg	681
0500RS					6.5			49		22.7kg	681
Terpolymers-low unsaturation											
3250		33				2.3		55			900
5260		55				2.3		62			900
4260C		43				2.3		55			900
6160D		63					1.2	64			1000
Terpolymers-medium unsaturation											
5465		53				4.0		64	50		900
2450		28				4.1		48			1000
4465		48				4.1		56	50		1000
2470E		22				4.2		69			900
2470S		25				4.2		69		quasi friable	1000
2470C		22				4.5		70.5			750
4450		46				4.3		52			1000
4450S		42				4.3		52			1000
6470C		63				4.8		64		quasi friable	750
5467C		52				4.5		58	75		900
5469C		52				4.5		58	100		900
3470		36				4.6		68		quasi friable	1000
5470C		55				4.6		66		friable	750
6471		65				4.7		67	15	quasi friable	1000
7470		70				4.7		67		friable	750
8570C		80				5.0		66		quasi friable	900
4577		46				5.1		66	75		1000
8550C		80				5.5		48		quasi friable	900
13561C		(130)		92		5.5		56	15	friable	750
4460D		46					4.5	58			1000
Terpolymers-high unsaturation											
2650		25				6.0		53			1000
2650C		25				6.0		46			750
9650C				60		6.5		51			900
10660C				66		6.5		56		friable	900
10675C				67		6.5		65			900
Terpolymers-very high unsaturation											
7752C				53		7.5		45	20		900
2750		28				7.8		48			1000
4869C		48				8.7		62	100		900
3973		34				9.0		66	30		1000
6951C		63				9.0		44	15		750
6950C		65				9.0		44			750
9950C				60		9.0		44			750
10950C				66		9.0		52			750
3960		35				11.0		56			900
Keltan Eco grades											
Keltan Eco 5470		55				4.6		70		friable	750
Keltan Eco 6950		65				9.0		48			750
Keltan Eco 8550		80				5.5		55			750

Suffix:

C = ACE

Q = Slurry

D = DCPD

V = VNB

L = Low Mooney

P = Pellets

R = Rex

S = Specialty

China Changzhou grades

Keltan 2650C

Keltan 2470C

Keltan 4260C

Keltan 4869C

Keltan 5470C

Keltan 5467C

Keltan 6470C

Keltan 6950C

Keltan 8550C

Keltan 9950C

Keltan 10660C

Keltan 10675C

Keltan 10950C

Keltan 13561C