

	Description	Description(和訳)	Raw Color	G.E. Brightness	pH	Specific Gravity	Surface Area (m2/g)	Median Particle size (μ)	Oil Absorption	Others
Amlok 321	Mineral Air Float Kaolin	アミノシラン処理をした風簾クレイです	White	70-80	7-9	2.6	22-26	0.3		
Mercap 100	Mineral Air Float Kaolin	メルカプトシラン処理をした風簾クレイです	White	70-80	4-5	2.6	22-26	0.3	33-38	
Mercap 200	Mineral Air Float Kaolin	メルカプトシラン処理をした風簾クレイです	White	70-80	4-5	2.6	22-26	0.3	33-38	Sharper particle size distribution than Mercap 100
Suprex	The hard kaolin, Suprex, has gained worldwide acceptance as the premier kaolin filler for the rubber industry. Higher modulus, tensile strength, tear resistance, abrasion resistance, and green strength are just a few of the benefits from using Suprex.	風簾クレイです。ゴムの補強硬化があります。	White		4-5.5	2.6		0.3		