



PIGMENTS FOR PLASTICS/塑料颜料

颜色 color	产品名称 Product Name	索引号 (Color index No)	牢度性能 Resistance				应用领域 Applications						
			耐热 (Heat Resistance in J)	耐光 (Lightfastness)	耐迁移 (Migration Resistance)	比重 (Density)	聚氯乙烯 (PVC)	聚丙烯 (PP)	纤维 (Fibre)	聚酰胺 (PA)	其它 PS,PC,PA	皮革 (PU)	
红色 RED	耐晒大红GN Lilyperm Red GN	C.I.P.R. 48:1	260	6	4	1.8	○	◎			○		
	耐晒大红BHNP Lilyperm Red BHNP	C.I.P.R. 48:1	260	6	5	1.8	◎	◎			◎		
	耐晒大红259 Lilyperm Red 259	C.I.P.R. 48:2	220	6	5	1.8	○	○			○		
	耐晒大红4827 Lilyperm Red 4827	C.I.P.R. 48:2	220	6	5	1.8	○	○			○		
	耐晒大红BH-2BP Lilyperm Red BH-2BP	C.I.P.R. 48:2	220	6	5	1.6	◎	◎	◎	◎			
	耐晒大红BH-2BPE Lilyperm Red BH-2BPE	C.I.P.R. 48:2	220	6	5	1.8	◎	◎	◎	◎			
	耐晒大红BH-2BSP Lilyperm Red BH-2BSP	C.I.P.R. 48:3	220	6	5	1.6	◎	◎	◎	◎			
	金光红OF-08 Lilyperm Red OF-08	C.I.P.R. 53:1	260	5	5	1.8	○	○			○		
	金光红OF-09 Lilyperm Red OF-09	C.I.P.R. 53:1	260	5	5	1.8	○	○			○		
	金光红CP Lilyperm Red CP	C.I.P.R. 53:1	260	5	5	1.6	◎	◎	○	◎			
	金光红CPB Lilyperm Red CPB	C.I.P.R. 53:1	260	5	5	1.6	◎	◎	◎	◎			
	金光红CPY Lilyperm Red CPY	C.I.P.R. 53:1	260	5	5	1.6	◎	◎	◎	◎			
	金光红5321 Lilyperm Red 5321	C.I.P.R. 53:1	260	5	5	1.6	◎	◎	○	◎			
	金光红5322 Lilyperm Red 5322	C.I.P.R. 53:1	260	5	5	1.6	◎	◎	○	◎			
	金光红5322A Lilyperm Red 5322A	C.I.P.R. 53:1	260	5	5	1.6	◎	◎	○	◎			
	金光红5322B Lilyperm Red 5322B	C.I.P.R. 53:1	260	5	5	1.6	◎	◎	○	◎			
	立索尔洋红BHN Lilyrubine BHN	C.I.P.R. 57:1	220	5	5	1.7	◎	◎			◎		
	立索尔洋红BHD Lilyrubine BHD	C.I.P.R. 57:1	220	5	5	1.7	◎	◎			◎		
	立索尔洋红BH-4BP Lilyrubine BH-4BP	C.I.P.R. 57:1	220	5	5	1.7	◎	◎	◎	◎			
	喹吡啶酮红1102B Lilyfast Red 1102B	C.I.P.R. 122	300	8	5	1.5	◎	◎	◎	◎	○	◎	
	喹吡啶酮红1103B Lilyfast Red 1103B	C.I.P.R. 122	300	8	5	1.5	◎	◎	○	◎	○	◎	
	永固红BH-2RK Lilyfast Red BH-2RK	C.I.P.R. 170	260	8	3	1.5		○		○		○	
	永固红BH-3RK Lilyfast Red BH-3RK	C.I.P.R. 170	260	7	3	1.5		○		○		○	
	永固红BH-5RK Lilyfast Red BH-5RK	C.I.P.R. 170	260	7	3	1.5		○		○		○	
	坚固红A3B Lilyfast Red A3B	C.I.P.R.177	300	8	5	1.5	○	○	○	○	○	○	○
	DPP红-D20 Lilyfast DPP Red D20	C.I.P.R. 254	300	8	5	1.6	◎	◎	◎	◎	○	◎	
	DPP红-D20S Lilyfast DPP Red D20S	C.I.P.R. 254	300	8	5	1.6	◎	◎	◎	◎	○	◎	

颜色 color	产品名称 Product Name	索引号 (Color index No)	牢度性能 Resistance				应用领域 Applications						
			耐热 (Heat Resistance in J)	耐光 (Lightfastness)	耐迁移 (Migration Resistance)	比重 (Density)	聚氯乙烯 (PVC)	聚丙烯 (PP)	纤维 (Fibre)	聚酰胺 (PA)	其它 PS,PC,PA	皮革 (PU)	
红色 RED	DPP红-D20-8 Lilyfast DPP Red D20-8	C.I.P.R. 254	300	8	5	1.6	◎	◎	◎	◎	○	◎	
	DPP红DB Lilyfast DPP Red DB	C.I.P.R. 254	300	8	5	1.6	◎	◎	◎	◎	○	◎	
	DPP红D28 Lilyfast DPP Red D28	C.I.P.R. 254	300	8	5	1.6	◎	◎	◎	◎	○	◎	
橙色 ORANGE	永固桔黄B-96 Lilyperm Orange B-96	C.I.P.O. 13	200	6	2	1.6		○					
	永固橙TR-139 Lilyfast Orange TR-139	C.I.P.O. 34	220	6	3	1.6		○		○			
	永固橙BH-HL Lilyfast Orange BH-HL	C.I.P.O. 36	260	7~8	5	1.6	◎	◎	○	◎	○	◎	
黄色 YELLOW	联苯胺黄OF-15 Lilyperm Yellow OF-15	C.I.P.Y. 12	200	6	2	1.5		○					
	联苯胺黄OF-15C Lilyperm Yellow OF-15C	C.I.P.Y. 12	200	6	2	1.5		○					
	永固黄1148 Lilyperm Yellow 1148	C.I.P.Y. 13	200	6	3	1.5		○					
	永固黄1148A Lilyperm Yellow 1148A	C.I.P.Y. 13	200	6	3	1.5		○					
	永固黄G-16 Lilyperm Yellow G-16	C.I.P.Y. 14	200	6	2	1.6		○					
	永固黄G-16B Lilyperm Yellow G-16B	C.I.P.Y. 14	200	6	2	1.6		○					
	永固黄277 Lilyfast Yellow 277	C.I.P.Y. 83	200	7	4~5	1.7	◎	○	○	○			
	永固黄8310 Lilyfast Yellow 8310	C.I.P.Y. 83	200	7	4~5	1.7	◎	◎	◎	○			
	永固黄8310A Lilyfast Yellow 8310A	C.I.P.Y. 83	200	7	4~5	1.7	◎	◎	◎	○			
	永固黄8311 Lilyfast Yellow 8311	C.I.P.Y. 83	200	7	4~5	1.7	◎	◎	◎	○			
	永固黄8311A Lilyfast Yellow 8311A	C.I.P.Y. 83	200	7	4~5	1.7	◎	◎	◎	○			
	颜料黄BH-G70 Lilyfast Yellow BH-G70	C.I.P.Y.139	200	7	5	1.7	◎	◎	◎	◎	○	○	
	颜料黄BH-G41 Lilyfast Yellow BH-G41	C.I.P.Y.139	200	7	5	1.7	◎	◎	◎	◎	○	○	
	永固黄BH-1504 Lilyfast Yellow BH-1504	C.I.P.Y. .150	260	8	5	1.8	◎	○	○	○	○	○	
	永固黄BH4G Lilyfast Yellow BH4G	C.I.P.Y. .151	240	7~8	5	1.6	◎	◎	○	◎	○	◎	
	永固黄BH3G Lilyfast Yellow BH3G	C.I.P.Y. .154	220	7~8	4	1.6	◎	◎	○	◎	○	○	
紫色 VIOLET	喹吡啶酮紫BH-201 Lilyfast Violet BH-201	C.I.P.V. 19	300	7~8	5	1.8	◎	◎	○	◎	○	◎	
	永固紫HR-256 Lilyfast Violet HR-256	C.I.P.V. 23	250	7~8	4~5	1.8	◎	◎	○	◎	○	○	
	永固紫HR-256P Lilyfast Violet HR-256P	C.I.P.V. 23	250	7~8	4~5	1.8	◎	◎	○	◎	○	○	
蓝色 BLUE	酞菁蓝156 Lilyfast Blue 156	C.I.P.B. 15:3	300	7~8	5	1.8	◎	◎	○	◎	○	◎	
绿色 GREEN	酞菁绿311 Lilyfast Green 311	C.I.P.G. 7	300	7	5	1.8	◎	◎	○	◎	○	◎	

所有关于我们产品的技术指标及推荐应用领域，均是基于我们目前对该产品的认识，客户在投入使用前，应做必要的实验。
Our products specifications and application information are based upon our current knowledge,customers must do the necessary test of individual product before put it into application.

◎ 主要用途 Main use ○ 建议使用 Suggest using



百合花集团股份有限公司

LILY GROUP CO., LTD

地址: 中国浙江省杭州市钱塘区临江街道经五路1768号

电话: 0571-82961666

销售热线: 0571-82963567 82965880 82965122

传真: 0571-82962000

Add : No.1768,linjiang Street,qiantang District,hangzhou City,zhejiang Province,china. 311228

Sales Phone: 0086-571-82963567 0086-571-82963680 Fax: 086-571-82962000

E-mail: Sales@lilychem.com

Web: www.lilychem.com

LILY GROUP
2023.08